

WOLFRACOAT C Spray

High-temperature lubricating paste



Your benefits at a glance

- Easier assembly and disassembly of power-locking connections
- Reliable lubrication under mixed-friction and high-load conditions owing to ageing-resistant solid lubricants

Your requirements - our solution

Wolfracoat C Spray is a grey high-temperature lubricating paste containing metal solid lubricant pigments (e.g. copper, graphite). Wolfracoat C Spray counteracts excessive friction, wear and seizing at lubricating points subject to high loads. Wolfracoat C Spray forms a thermally stable lubricating film. At temperatures above 200 °C, the solid lubricants remain in the friction points and protect against tribocorrosion and fretting of e.g. fits up to 1200 °C.

Application

Wolfracoat C Spray is suitable for use as an assembly paste to lubricate power-locking connections and low-speed (plain) bearings subject to high temperatures. Typical applications are in power plants, the steel industry, cement manufacture and similar industrial areas.

Application notes

Prior to initial lubrication clean all friction points thoroughly and apply the product in an even, thin and extensive layer. Shake spray can well before use and provide for adequate ventilation while spraying. Do not spray against naked flame or onto hot or incandescent objects. Observe additional instructions for use in material safety data sheet and on can label.

Material safety data sheets

Material safety data sheets can be requested via our website www.klueber.com. You may also obtain them through your contact person at Klüber Lubrication.

Pack sizes	WOLFRACOAT C Spray
Aerosol can 400 ml	+

Characteristics	WOLFRACOAT C Spray
Article number	081150
Composition	solid lubricant
Composition, thickener	silicate
Composition, type of oil	synthetic hydrocarbon oil
Colour space	grey
Service temperature, lower limit	-30 °C
Service temperature, upper limit	1200 °C
Worked penetration, DIN ISO 2137 / ASTM D217, 25°C, lower limit	270 0.1 mm
Worked penetration, DIN ISO 2137 / ASTM D217, 25°C, upper limit	310 0.1 mm
Shear viscosity, Klüber method: PN 008@DIN 53019-1, equipment: rotational viscometer, 25°C, 300 s ⁻¹ , lower limit	5000 mPas

WOLFRACOAT C Spray

High-temperature lubricating paste



Characteristics	WOLFRACOAT C Spray
Shear viscosity, Klüber method: PN 008@DIN 53019-1, equipment: rotational viscometer, 25°C, 300 s ⁻¹ , upper limit	9000 mPas
Kinematic viscosity of the base oil, DIN EN ISO 3104 / DIN 51562-1 / ASTM D445 / ASTM D7042, 40°C	approx. 110 mm ² /s
Four-ball tester, welding load, DIN 51350-4	≥ 3000 N
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx.	24 months

Klüber Lubrication – your global specialist

Innovative tribological solutions are our passion. Through personal contact and consultation, we help our customers to be successful worldwide, in all industries and markets. With our ambitious technical concepts and experienced, competent staff we have been fulfilling increasingly demanding requirements by manufacturing efficient high-performance lubricants for more than 90 years.

Klüber Lubrication München GmbH & Co. KG /
Geisenhausenerstraße 7 / 81379 München / Germany /
phone +49 89 7876-0 / fax +49 89 7876-333.

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication München GmbH & Co. KG. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication München GmbH & Co. KG and if source is indicated and voucher copy is forwarded.